



AMERIPOLISH® SureLock™ CONCRETE DYE

PRODUCT DESCRIPTION

Concrete dye concentrate for interior use.

RECOMMENDED PRODUCT USE

Coloring concrete; especially designed for diamondpolished concrete. For optimum performance, use Ameripolish® SureLock™ Dye with with 3D HS Hybrid Silicate Densifier, 3D SP Stain Protect and/or SR2 Penetrating Sealer together to lock in colors for long term beauty. Dye concentrate may be diluted in acetone or water. Product can be used with densifiers and stain protectors from other manufacturers; however, optimum stain resistance and color retention cannot be assured.

FEATURES

SureLock™ Dye provides consistent color that penetrates the surface layer deeply, and is reactive with concrete, forming a bond that locks color into slab, minimizing color migration or diffusion. • Bonds with the other SureLock™ Color System components to protect color in slab. • Is available in a broad range of vibrant colors. Contains UV stabilizer to help protect colorants in concrete against fading. • Liquid concentrate eliminates 3-hour wait to dissolve dye required by other products. VOC compliant (< 40g/L)

PREPARATION

SURFACES MUST BE CLEAN AND DRY BEFORE APPLICATION OF THE DYE. NEW SLABS MUST HAVE CURED FOR AT LEAST 28 DAYS BEFORE APPLICATION. For best results perform a moisture content test on both newly-poured and existing slabs. Slabs with a moisture content of 5 lbs. per foot or less show best performance (calcium chloride test per ASTM F1869). High moisture levels may affect performance of color. Do not apply if concrete is frozen, dirty or has standing water. Test surface absorbency with a light water spray – concrete surface should wet uniformly. If concrete does not wet uniformly, remove any surface contaminants with appropriate cleaning treatment or mechanical process. Surfaces should be clean, structurally sound, and free of all foreign materials including sealants, adhesives, bond breakers, curing compounds, curing agents, surface grease and oil, and construction debris. Ground or sanded surfaces should be vacuumed thoroughly. Acid-stained concrete should be neutralized and rinsed before application of dye.

DILUTION AND COVERAGE

Mixing SureLock™ Dye: SureLock™ Dye concentrate can be diluted with acetone or water: Mix the contents within 8 oz (.23 L) bottle of SureLock™ Dye concentrate with 1 gal (3.8 L) acetone OR 8 oz (.23 L) SureLock™ Dye concentrate with 1 gal (3.8 L) water Mix the contents within 32 oz (.9 L) bottle of SureLock™ Dye concentrate with 5 gal (18.9 l) acetone OR 32 oz (.9 L) SureLock™ Dye concentrate with 5 gal (18.9 L) water Coverage varies depending on concrete mixture, porosity, and moisture content and on ambient conditions. Use test areas to determine appropriate application rate. As a starting point to determine coverage: 400 sf / gal (9.8 m² / L)

APPLICATION

Testing: Prior to starting project, apply SureLock™ Dye to sample area of each type of concrete to be treated, using applications procedures proposed for project. Confirm that concrete is receptive to dye or dye/densifier combination and that color is acceptable. **Project Conditions:** Ambient temperature during application should be 40-100°F (4-38°C). For SureLock™ System Equipment: Spray apply SureLock™ using low pressure sprayer with Patriot Gray #8 or similar conical mist tip with 8.4 gal/hr flow at 40 psi. (31.8 L /hr at 275.8 kPa), microfiber pad or similar microfiber floor finish applicator pad.

Application Instructions: 1. Grind up to 200-grit resin bond diamonds. (If not using a 200-grit step, grind up to 100-grit resins.)

2. Remove all dust and debris. If wet cleaning is performed, allow surfaces to dry.

3. Vacuum surface thoroughly.

4. Spray SureLock Dye to lightly wet surface without creating puddles. Apply in a consistent, overlapping circular motion, holding the wand approximately 12-18 inches above the surface. Dye will absorb into concrete more quickly in some places than others. This is normal and does NOT indicate that extra dye is needed.

5. For acetone-dye mixtures, immediately upon completion of application, run clear acetone through the pump and wand, followed by clean water. For waterdye mixtures, clean with water only. This is recommended between color changes and prior to storing the sprayer between jobs.

6. Allow surface to dry.

APPLICATION (cont'd from page 1)

7. Spray 3D HS in an overlapping motion. Avoid puddles. Product does not need vigorous scrubbing-in and will not form a gel. As product is absorbed into surface, apply additional product as needed until floor starts to reject the product. Over-application or puddles of excess material will lengthen drying time, and may produce white surface residue that must be removed immediately.
8. Clean equipment with fresh water before product dries. Overspray on unprotected surfaces should be immediately washed off.
 9. Allow surface to dry.
 10. Polish up to 400-grit resin bond diamonds.
11. Apply SureLock Dye again for maximum color, using same method as step 4.
 12. Clean sprayer as in step 5.
 13. Allow surface to dry.
14. Remove dye residue with an autoscrubber fitted with a white pad and water. Perform white-rag test to assure that residue is removed. Wipe a dry white rag across the floor. A light tinge of residual color on the rag is acceptable, but any strong color indicates that excessive dye must still be removed. Unremoved dye residue will load resin diamonds and may produce undesirable marks.
 15. Polish with 800-grit resins, and 1500-grit or 3000-grit if desired.

Absorption-resistance of densified surface continues to develop over 7 days. However, concrete, even after becoming densified and polished, is still a porous substrate. Densifiers can take 2-6 months to attain full densification.

NEXT STEPS Apply 3D SP Stain Protector or SR2 Penetrating Sealer following manufacturer's instructions to complete protection and enhance appearance. 3D SP Stain Protector or SR2 Penetrating Sealer is strongly recommended for all colored polished concrete to protect color from staining or acidic etching agents, as well as minimizing color loss through diffusion or dispersion. Chemical resistance gains strength over time. Avoid chemical exposure for first 7 days.

Clean tools and equipment immediately with water. Always remove rundown and spills immediately.

CLEANUP

STORAGE AND HANDLING

MAINTENANCE

Keep containers upright and tightly sealed. Do not allow product to freeze, nor use if it has been frozen. Keep under 110° F.

Remove dust and debris with microfiber pad or dry mop. Buff dry with high speed burnisher to enhance sheen. Spills of staining agents or acidic etching agents including acidic food substances (e.g. vinegar, pickle juice) should be cleaned up immediately to minimize damage to surface. Surface should be cleaned regularly using an automatic floor scrubber with Ameripolish® PoliSmart CS Cleaner mixed with water according to manufacturer's directions. Ameripolish® PoliSmart CS Cleaner is a pH neutral formula that will not damage concrete and replenishes the Stain Protector application to maintain liquid and chemical resistance. DO NOT use with acidic cleansers. Autoscrubber should be fitted with non-aggressive cleaning tools such as brushes. Do not perform regular maintenance with aggressive pads such as diamond-impregnated pads or other abrasives. Use of aggressive pads will wear away stain protection and may, in time, wear away color from concrete surface. Renew 3D SP Stain Protector or SR2 Penetrating Sealer application every two years or more often depending on wear and usage conditions.

SAFETY PRECAUTIONS

WARNING – Before using or handling this material, read the MSDS and Warranty. For dilution with 3D HS Densifier, see Safety Precautions on Densifier TDS. For Dilution with Acetone: SURELOCK™ CONCRETE DYES ARE HIGHLY FLAMMABLE WHEN MIXED WITH ACETONE. GREAT CARE SHOULD BE TAKEN WHEN USING THIS PRODUCT! Acetone will produce vapors that are highly flammable and can be harmful to the applicator's health. Make sure rooms are properly ventilated. Open windows and use fans to achieve air movement. Non-explosive exhaust devices may be required in areas with poor ventilation. Make absolutely certain no source of open flame is present. Pilot lights, heaters, cigarettes, and electric tools should not be used or turned on until all vapors have dissipated. Always wear a carbon filter respirator, eye protection, and chemical resistant gloves. Devices are available to measure acetone vapors. Avoid contact with skin, eyes, and clothing: may permanently stain. KEEP OUT OF REACH OF CHILDREN. DO NOT TAKE INTERNALLY.

FIRST AID

Ingestion: DO NOT induce vomiting. Drink large quantities of water or milk. Seek medical attention immediately. **Eye Contact:** Remove contact lenses. Immediately flush eyes for 15 minutes in clear running water; hold eyelids open. Seek medical attention if irritation persists after flushing. **Skin Contact:** Wash affected area with soap and water. If irritation persists, seek medical attention. **Inhalation:** remove victim to fresh air. If necessary, use artificial respiration to support vital functions. Seek medical attention if adverse effect continues after removal to fresh air.

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR

NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR LIABILITY

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Listed physical properties are typical and should not be construed as specifications. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, REGARDING SUCH OTHER INFORMATION, THE DATA ON WHICH IT IS BASED, OR THE RESULTS YOU WILL OBTAIN FROM ITS USE. NO WARRANTY IS MADE, EXPRESSED OR IMPLIED, THAT OUR PRODUCT SHALL BE MERCHANTABLE OR THAT OUR PRODUCT SHALL BE FIT FOR ANY PARTICULAR PURPOSE. NO WARRANTY IS MADE THAT THE USE OF SUCH INFORMATION OR OUR PRODUCT WILL NOT INFRINGE UPON ANY PATENT. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may CAUSE SERIOUS PHYSICAL INJURY. BEFORE USING, READ THE MATERIAL SAFETY DATA SHEET AND FOLLOW ALL PRECAUTIONS TO PREVENT BODILY HARM.