



## TECHNICAL DATA SHEETS

# ELASTATHANE AR

### PRODUCT DESCRIPTION

Sanitred's Elastathane AR is a 100% solids, single component, aromatic binder for rubber EPDM granules and SBR Base.

**STANDARD COLORS:** Clear

#### CURE SCHEDULE (70°)

**POT LIFE (5 GAL Volume)** Long

**TACK FREE (DRY TO TOUCH)** 20-24 hours depending on Humidity

**RECOAT OR TOPCOAT** N/A

**LIGHT FOOT TRAFFIC** 24-48 hours

**FULL CURE** 28 days

#### COVERAGE

Recommended for binding EPDM rubber.

**COVERAGE PER GALLON:**

Mix 1 to 1 w/approved solvent: 180- 220 square feet per gallon rolled as primer. 40' per gallon mixed with epdm at 3/8"

**MIX RATIO:**

4 Parts EPDM rubber to 1 part binder.

**RECOMMENDED FILM THICKNESS:**

5/16"-3/8"

**PACKAGING INFORMATION:**

5 Gallon Pails, \*Special order 50 Gal Drums, 250 Gal Totes

### PHYSICAL PROPERTIES

**FLEXURAL STRENGTH:** N/A

**COMPRESSIVE STRENGTH:** N/A

**TENSILE STRENGTH:** 2000+/- 200psi @ ASTM D-412

**Weight:** 8.95 # Per Gal

**ADHESION:** N/A

**VISCOSITY:** 2800 (+/-500) cps

**ABRASION RESISTANCE:** N/A

**ULTIMATE ELONGATION:** 500-700 varies by EPDM ASTM D-412

**HARDNESS:** N/A

**VOLATILE ORGANIC CONTENT:** N/A

**SHELF LIFE:** 1 years in unopened containers

### LIMITATIONS

Surface to be coated must be clean, dry, and free from moisture. Best results when applied in temperatures over 55 degrees Fahrenheit and no freezing within 48 hours.

Has little to no UV stability and surface will yellow in the UV. In most cases the surface of the EPDM rubber that has been mixed with Elastathane AR will wear away in 3-6 months leaving the natural color of the EPDM rubber. No color change is noticeable when mixed with Black EPDM rubber.

**WARNING :** This product contains Isocyanates.

## INSTRUCTIONS

**Primer:** Mix 1:1 with an approved solvent and apply with a roller for a coverage rate of 180- 220 sq ft per mixed gallon depending on concrete texture/porosity.

**Binding with EPDM Rubber:** Mix 4 parts rubber to one part Elastathane AR Binder by weight.

One Gallon of Elastathane AR = 8.95 #'s per gal. Mix with 35.8 pounds of EPDM Rubber. Refer to the TCP Training manual or Tech support for specific application instructions.

A test patch is recommended to assure suitability of this system with your substrate.

**SURFACE PREPARATION:** Remove any loose crumbly substrate; make sure the substrate is clean, dry, and free of any previous applied products.

Refer to the TCP Training manual and the ICRI standards for proper surface preparation.

**CLEANUP:** Tools used can be cleaned with soapy water, acetone, or xylene.

## NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR

The Concrete Protector (Division of Incredible Products, LLC), warrant that all products are assembled under rigorous quality assurance specifications and that all information supplied is exact to the best of our knowledge. All information supplied is not to be taken as a warranty, but for you to conduct your own test to determine if the given product is suitable for your distinct purpose. The following list of properties should not be interpreted as specifications. CONVEYED OR SUGGESTED, NO WARRANTY IS BUILT UPON ANY DISCOVERED RESULTS OR INFORMATION YOU WILL OBTAIN DURING USE. CONVEYED OR SUGGESTED NO WARRANTY IS BUILT THAT THE GIVEN PRODUCT SHALL BE MARKETABLE OR THAT THE GIVEN PRODUCT WILL BE FIT FOR ANY DISTINCT PURPOSE. NO WARRANTY IS BUILT UPON SAID INFORMATION OR THAT THE GIVEN PRODUCT WILL NOT INFRINGE UPON ANY PATENT. The Concrete Protector is NOT liable for, direct or indirect, inadvertent or consequential damages. The Concrete Protector's liability is and will only be limited to the net selling price of our products or, at our discretion, the replacement of our products. Upon delivery of our products, your acceptance means that you accept all terms of this warranty even if other documents and or purchase orders stray from the terms of this warranty. No representative, on our behalf, is permitted to make any representation, warranty, or assume liability with any sale of our products. OUR PRODUCTS CONTAIN CHEMICALS THAT CAN CAUSE SERIOUS PHYSICAL INJURY. BEFORE THE USE OF OUR PRODUCTS, READ ALL MATERIAL AND FOLLOW ALL LISTED PRECAUTIONS TO AVOID ANY BODILY HARM