



# TECHNICAL DATA SHEET

## EPOXY NEAT COAT

### PRODUCT

The Concrete Protector Neat Coat is a 100% solids, two-component, low VOC, Cycloaliphatic amine epoxy with excellent durability.

**STANDARD COLORS:** Clear

**OTHER COLORS ALSO AVAILABLE:** N/A

### CURE SCHEDULE (75°)

**POT LIFE (1.5 GAL Volume)** 25 Minutes

**TACK FREE (DRY TO TOUCH)** 8 hours

**RECOAT OR TOPCOAT** 10 hour Min  
20 hours Max

**LIGHT FOOT TRAFFIC** 24-30 hours

**FULL CURE** 7-10 days

### COVERAGE

Recommended for seamless high build applications and for use with our Metallic Marble system. *Because of the many uses of this product, be sure and discuss project ahead of time with one of our Business Development representatives to determine proper coverage rates.*

**COVERAGE PER GALLON:**

50 - 200 sq ft @ 32 - 8 mils for Primer  
50 - 200 sq ft @ 32 - 8 mils for Finish Coat

**MIX RATIO:** 2 to 1

**RECOMMENDED FILM THICKNESS:**

32 - 8 mils Prime Coat  
32 - 8 mils Finish Coat

**PACKAGING INFORMATION:**

1.5, 3, 7.5 and 15, 165, 750 Gallon Kits

### PHYSICAL PROPERTIES

**FLEXURAL STRENGTH:** N/A

**COMPRESSIVE STRENGTH:** 6500

**TENSILE STRENGTH:** 5400 psi@ ASTM D 638

**ADHESION:** N/A

**VISCOSITY:** Mixed 1000 CPS

**ABRASION RESISTANCE:** 0.10 mg loss

**ULTIMATE ELONGATION:** 6.6%

**HARDNESS:** D=86-90

**VOLATILE ORGANIC CONTENT:** 40 g/liter

**SHELF LIFE:** 1 year in unopened containers

### CHEMICAL RESISTANCE

REAGENT	RATING
METHANOL	A
MEK	A
70% SULFURIC ACID	A
SKYDROL B4	B
5% ACETIC ACID	B
BUTANOL	C
XYLENE	C
GASOLINE	C
ETHYLENE ALCOHOL	C
10% SULFURIC ACID	C
10% HCl	C
50% SODIUM HYDROXIDE	D
10% SODIUM HYDROXIDE	E

RATING KEY: A - NOT RECOMMENDED, B - 2 HOUR TERM SPLASH SPILL, C - 8 HOUR TERM SPLASH SPILL, D - 72 HOUR IMMERSION, E - LONG TERM IMMERSION.

NOTE: EXTENSIVE CHEMICAL RESISTANCE INFORMATION IS AVAILABLE THROUGH YOUR SALES REPRESENTATIVE.

## LIMITATIONS

**Due to High Chemical Resistance Cannot Top Coat with Polyaspartics or Graniseal (Exception: Our SLV P90 works well as a topcoat over Neat Coat)**

All new concrete must be cured 28 days.

Humidity may cause a haze visible in the sheen. When using a clear to topcoat this will disappear. Coverage rates depend upon many conditions, including application method, surface porosity, applicator.

Be aware that this product may be slippery when wet.

Do not apply at temps below 50F or above 85F

Application without using a moisture vapor barrier has a risk of detachment by hydrostatic pressure.

Neat Coat may darken the surface of many new and existing concrete substrates. Test prior to use.

*Do not apply a floor coating when the dew point temperature is within 5° F (3°C) of surface temperature.*

## INSTRUCTIONS

**PRODUCT MIXING:** Kits come premeasured. 2 Parts A to 1 Part B

**SURFACE PREPARATION:** Refer to the TCP Training manual and the ICRI standards for proper surface preparation.

**CLEANUP:** Use xylol

**FLOOR CLEANING:** Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

**RESTRICTIONS:** Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.

## NOTICE TO BUYER: DISCLAIMER OF WARRANTIES AND LIMITATIONS ON OUR

The Concrete Protector (Division of Incredible Products, LLC), warrant that all products are assembled under rigorous quality assurance specifications and that all information supplied is exact. All information supplied is not to be taken as a warranty, but for you to conduct your own test to determine if the given product is suitable for your distinct purpose. The following list of properties should not be interpreted as specifications. CONVEYED OR SUGGESTED, NO WARRANTY IS BUILT UPON ANY DISCOVERED RESULTS OR INFORMATION YOU WILL OBTAIN DURING USE. CONVEYED OR SUGGESTED NO WARRANTY IS BUILT THAT THE GIVEN PRODUCT SHALL BE MARKETABLE OR THAT THE GIVEN PRODUCT WILL BE FIT FOR ANY DISTINCT PURPOSE. NO WARRANTY IS BUILT UPON SAID INFORMATION OR THAT THE GIVEN PRODUCT WILL NOT INFRINGE UPON ANY PATENT. The Concrete Protector is NOT liable for, direct or indirect, inadvertent or consequential damages. The Concrete Protector's liability is and will only be limited to the net selling price of our products or, at our discretion, the replacement of our products. Upon delivery of our products, your acceptance means that you accept all terms of this warranty even if other documents and or purchase orders astray from the terms of this warranty. No representative, on our behalf, is permitted to make any representation, warranty, or assume liability with any sale of our products. OUR PRODUCTS CONTAIN CHEMICALS THAT CAN CAUSE SERIOUS PHYSICAL INJURY. BEFORE THE USE OF OUR PRODUCTS, READ ALL MATERIAL AND FOLLOW ALL LISTED PRECAUTIONS TO AVOID ANY BODILY HARM